



MAT GREEN

Applied to clear glass, the Mat Green film bestows a mat green tint to the glass without diminishing its transparent properties. It is the perfect way to enliven any interior glazing (such as partitions, shower screens, etc.) with a touch of colour.



SOLAR SCREEN® Warranty
5 YEARS



Storage from -5°C to +40°C
3 YEARS



REACH RoHS compliant
RESPECTED

WIDTHS AVAILABLE:

↔ **152 cm**

TECHNICAL DATASHEET

Data calculated based on film applied to clear glass 3 mm thick (*on double glazing 4-16-4)

| | |
|--|--------|
| Ultraviolet transmission | 1 % |
| Visible light transmission | 45 % |
| Reflection of external visible light | 8 % |
| Reflection of internal visible light | 8 % |
| Total solar energy rejected | 32 % |
| Total solar energy rejected 2* | 29 % |
| Solar ratio : | |
| Solar energy reflection | 9 % |
| Solar energy absorption | 43 % |
| Solar energy transmission | 48 % |
| Reduction in Solar Glare | 58 % |
| g-value | 0.69 |
| u-value | 5.7 |
| Shading coefficient | |
| Installation type : Internal application | |
| Roll length | 30,5 m |
| PET / PVC composition | PET |
| Thickness | 60 µ |

Colour : GREEN

MAINTENANCE INSTRUCTIONS

Soapy water solution (ref. 0805 Film on), do not clean for at least a month and do not apply any type of sticker or adhesive on the film.

Non-contractual data, SOLAR SCREEN® reserves the right to modify the composition of its films at any time. Consult our guarantee vouchers and our general conditions of sale.

INSTALLATION ADVICE

Vertical installation and on standard glass surface**

| | |
|--------------------------------|---|
| Clear single pane | ✓ |
| Tinted single pane | ! |
| Reflective tinted single pane | ✓ |
| Clear double pane | ! |
| Tinted double pane | ! |
| Reflective tinted double pane | ✓ |
| Gas-filled double pane - Low E | ! |
| STADIP EXT. clear double pane | ! |
| STADIP INT. clear double pane | ✗ |

✓ Yes ! Caution ✗ Not recommended

*Recommendations provided on the basis of a glazed surface covering up to 2.5m², contact us for definitive details or to obtain a thermal chock analysis report.